

**Table 1**

<b>HOLE</b>	<b>FROM (m)</b>	<b>TO (m)</b>	<b>INTERVAL (m)</b>	<b>GRADE (g/t Au)</b>
OKD-49	57.1	59.0	2.0	1.0
	77.1	77.5	0.4	2.0
	157.9	160.5	2.7	2.2
OKD-50	100.0	107.0	7.0	0.4
	47.1	50.0	2.9	2.7
<b>OKD-51</b>	<b>122.0</b>	<b>122.4</b>	<b>0.4</b>	<b>13.3</b>
	181.6	182.7	1.1	2.6
OKD-52	146.7	153.5	6.8	2.7
<i>Incl.</i>	<b>151.5</b>	<b>153.1</b>	<b>1.6</b>	<b>6.8</b>
OKD-52	283.4	285.0	1.6	6.9
<i>Incl.</i>	<b>283.4</b>	<b>284.1</b>	<b>0.7</b>	<b>15.3</b>
OKD-53	59.0	60.9	1.9	6.0
OKD-54	135.0	141.0	6.0	2.4
	<b>149.0</b>	<b>159.1</b>	<b>10.1</b>	<b>2.1</b>
<i>Incl.</i>	<i>149.0</i>	<i>152.1</i>	<i>3.1</i>	<i>4.1</i>
OKD-54	166.5	167.4	0.9	5.2
	196.4	196.8	0.4	5.4
	<b>291.3</b>	<b>294.4</b>	<b>3.2</b>	<b>8.4</b>
<b>OKD-54</b>	301.0	307.7	6.7	10.5
<i>Incl.</i>	<i>303.2</i>	<i>304.1</i>	<i>0.9</i>	<i>34.6</i>
<i>Incl.</i>	<i>306.9</i>	<i>307.7</i>	<i>0.8</i>	<i>42.7</i>

*Widths reported are drill indicated core length. True widths are estimated at 75% to 85% of core lengths for holes OKD-49 to OKD-54. Average grades are calculated with un-capped gold assays, as insufficient drilling has been completed to determine capping levels for higher grade intercepts. All holes are drilled at an angle of 60 degrees to the horizontal.*