



DRILL HOLE	FROM (metres)	TO (metres)	INT. (metres)	GRADE g/t Au
GDD-136	443.0	468.7	25.7	1.6
<i>Incl.</i>	456.5	458.8	2.3	6.3
GDD-137	492.0	503.5	11.5	2.7
<i>Incl.</i>	495.0	497.7	2.7	7.1
GDD-138	177.0	222.0	45.0	0.6
GDD-139	358.0	367.0	9.0	1.2
GDD-140	124.5	127.5	3.0	4.7
And	242.5	277.0	34.5	2.0
<i>Incl.</i>	264.0	277.0	13.0	4.7
GDD-141	205.0	206.5	1.5	20.2
And	369.0	399.5	30.5	1.9
<i>Incl.</i>	372.0	387.0	15.0	2.4
And	396.0	399.5	3.5	4.9
And	409.0	411.4	2.4	11.3
GDD-142	369.0	378.0	9.0	4.4
<i>Incl.</i>	373.8	376.5	2.7	10.3
GDD-143	451.5	486.5	35.0	1.1
<i>Incl.</i>	479.7	482.0	2.3	7.3
GDD-144	111.0	114.0	3.0	18.8
And	153.0	176.0	23.0	4.4
<i>Incl.</i>	167.0	176.0	9.0	8.5
GDD-145	439.5	445.5	6.0	3.0
<i>Incl.</i>	442.5	445.5	3.0	5.1
GDD-146	180.5	189.5	9.0	2.0
GDD-147	49.0	57.5	8.5	3.7
<i>Incl.</i>	49.0	50.0	1.0	28.8
And	506.0	547.0	41.0	1.0
<i>Incl.</i>	528.0	530.5	2.5	8.9



GDD-148		No Significant Assays		
GDD-149	102.0	107.5	5.5	1.2
And	120.5	128.0	7.5	1.2
GDD-150	167.0	173.0	6.0	1.2
GDD-151	150.5	189.5	39.0	0.6
GDD-152	78.0	80.5	2.5	3.1
And	169.0	170.0	1.0	3.4
And	255.7	265.5	9.9	1.1
GDD-153	88.5	90.0	1.5	3.1
GDD-154	91.5	114.0	22.5	0.7
GDD-155	271.1	275.8	4.7	2.6
GDD-156	91.5	107.4	15.9	1.9
<i>Incl.</i>	97.8	103.3	5.6	3.4
GDD-157	270.1	288.5	18.4	2.0
<i>Incl.</i>	282.5	287.0	4.5	6.0
GDD-158		No Significant Assays		
GDD-159		No Significant Assays		
GDD-160	110.0	111.5	1.5	1.8
GDD-160	212.5	222.0	9.5	5.9
<i>Incl.</i>	217.0	222.0	5.0	10.7
GDD-161	206.0	226.4	20.4	2.3
<i>Incl.</i>	220.5	225.0	4.5	8.2
GDD-162	168.0	202.0	34.0	0.6
GDD-163	214.0	225.5	11.5	0.7
GDD-164	166.5	172.0	5.5	2.4
<i>Incl.</i>	166.5	168.0	1.5	7.9



GDD-164	199.0	205.0	6.0	3.7
<i>Incl.</i>	<i>199.0</i>	<i>202.0</i>	<i>3.0</i>	<i>7.2</i>
And	236.0	244.0	8.0	0.7
And	266.0	285.0	19.0	2.2
<i>Incl.</i>	<i>274.5</i>	<i>277.5</i>	<i>3.0</i>	<i>8.4</i>
GDD-165	158.0	159.5	1.5	27.3
And	194.5	195.2	0.7	16.0
GDD-166A	172.0	181.0	9.0	1.6
And	311.3	329.7	18.4	2.0
<i>Incl.</i>	<i>326.5</i>	<i>329.7</i>	<i>3.2</i>	<i>8.2</i>
GDD-167	315.0	330.5	15.5	4.9
<i>Incl.</i>	<i>324.5</i>	<i>329.1</i>	<i>4.6</i>	<i>13.7</i>
GDD-168	225.0	249.1	24.1	0.9
GDD-169B	319.5	327.2	7.7	4.0
<i>Incl.</i>	<i>324.0</i>	<i>327.2</i>	<i>3.2</i>	<i>8.0</i>
GDD-170	132.0	146.5	14.5	1.2
GDD-171	189.0	193.4	4.4	10.8
And	218.5	219.5	1.0	11.2
And	351.0	398.0	47.0	0.8
<i>Incl.</i>	<i>397.0</i>	<i>398.0</i>	<i>1.0</i>	<i>9.7</i>
GDD-172	No Significant Assays			
GDD-173	93.5	95.0	1.5	88.0
And	274.0	307.0	33.0	1.1
<i>Incl.</i>	<i>281.5</i>	<i>287.5</i>	<i>6.0</i>	<i>2.5</i>
GDD-174	399.0	406.1	7.1	2.4
<i>Incl.</i>	<i>402.0</i>	<i>405.5</i>	<i>3.5</i>	<i>4.2</i>

The intercepts reported are down-hole widths. True widths are estimated between 75% and 85% of reported down-hole widths. Gold grades are uncapped.